RecyClass **PP Crates & Pallets**

		FULL COMPATIBILITY	LIMITED COMPATIBILITY	NON-COMPATIBILITY
	MATERIAL COMPOSITION (AMOUNT OF PO IN THE PACKAGING)	A >= 95%, B >= 80% and all packaging features are FULLY compatible with recycling	C >= 70% and all packaging features are FULLY compatible with recycling	Non-recyclable < 70% and all packaging features are FULLY compatible with recycling
	DESCRIPTION (TEST PROTOCOL)	Materials that passed the testing protocols with no negative impact*** OR materials that have not been tested (yet), but are known to be acceptable in PE-HD or PP recycling	Materials that passed the testing protocols if certain conditions are met*** OR materials that have not been tested (yet), but pose a low risk of interfering with PE-HD or PP recycling	Materials that failed the testing protocols OR materials that have not been tested (yet), but pose a high risk of interfering with PE-HD or PP recycling
	DESCRIPTION (METHODOLOGY)	In case of at least one limited compatibility one penalty is applied, lowering the recyclability class from A to B or from B to C	In case of at least one limited compatibility one penalty is applied, lowering the recyclability class from C to non-recyclable	Non-recyclable
MAIN BODY	MATERIALS*	PP	PE <= 10 wt%	Multilayers PP with PLA, PVC, PS, PET, PETG; PE > 10 wt%
	COLOURS	Light colours	Dark colours	Non NIR-detectable colours
	ADDITIVES	Additives that are unavoidable in processing (stabilizers, antioxidants, lubricants, nucleating agents, peroxides) and density remains < 0.97 g/cm^3	Mineral fillers (CaCO3, talc) not increasing density more than 0,97 g/cm³	Additives changing the material density > 1 g/cm³, Flame-retardant additives, plasticizers, Bio-/oxo-/photodegradable additives
ATTACHMENTS	COVERING SYSTEM	PP	PE	Any other
DECORATION	INKS	Non-bleeding inks compliant with EuPIA Exclusion Policy		Inks that bleed, Inks non-compliant with EuPIA Exclusion Policy, PVC binders
	LABELS MATERIALS**	Low size labels in PP (with density < 1 g/cm³); Avoid multiple labels	Low size labels in PE, PO (with density < 1 g/cm^3); Low size labels in PET, PETG, PLA, PS (all with density > 1 g/cm^3); Low size labels in Paper without fibreloss; Low size PO-foamed labels; Low size In-Mould-Labels in the same material as the main body (except bleeding inks); Avoid multiple labels	Labels that hinder the recognition of the PP; Labels in non PO-materials with density < 1 g/cm³; Paper labels with fibreloss during recycling process; Aluminium; Metallised labels; PVC; Cardboard or paper in In-Mould-Labels.
	ADHESIVES FOR LABELS	Water soluble or water releasable adhesive (@ less than 40°C)	Non-water soluble or non-releasable adhesive $\underline{\text{approved}}$ by RecyClass in combination with filmic PO labels	Non water soluble or non water releasable adhesives
	DIRECT PRINTING	Laser marked	Direct printing (low extent of printing)	

RECYCLED CONTENT: No change in the recyclability assessment. A separate 'Recycled Plastics Traceability Certification' based on a Chain of Custody approach is available with RecyClass.

Last update: July 2023

Phone: +32 2 786 39 08 info@recyclass.eu www.recyclass.eu

^{*} Polymer resin can be either fossil-or bio-based, virgin or recycled . If different grades of the same polymer are present, weights should be cumulated.

^{**} The surface coverage of a low size label is currently under definition.
*** Approved technologies can be found here